Available online at www.pelagiaresearchlibrary.com



**Pelagia Research Library** 

Der Chemica Sinica, 2017, 8(2):282-290



# Novel Green Soybean Oil Derivatives as Corrosion Inhibitors for Mild Steel at 0.5 N HCl

# Rabab M. Nasser<sup>1,2</sup>\*

<sup>1</sup>Egyptian Petroleum Research Institute, Department of Petroleum Applications, Nasr city, Cairo, Egypt <sup>2</sup>Jazan University, Faculty of Science and Arts, Samtah, Chemistry Department, Saudi Arabia

# ABSTRACT

Novel four green corrosion inhibitors were prepared via amination of brominated soybean oil using different types of amines (urea, thiourea, p- toluidine, and 3-amino benzoic acid). The prepared compounds were elucidated using FT-IR and 1H-NMR; they were evaluated as corrosion inhibitors at different temperatures (308, 318, 328 and 338 K) using weight loss method and chemical analysis method. The corrosion tests proved that the prepared compounds exhibit excellent corrosion inhibition properties at acidic medium.

**Keywords:** Aminated soybean derivatives, Mild steel, Green corrosion inhibitors, Weight loss method, Chemical analysis method

# INTRODUCTION

The soybean seeds are composed of 40% protein and 20% oil content, and most importantly soybean oil accounts for approximately 30% of the world's vegetable oil supply [1]. Although soybean oil is primarily used as edible oil, there is a continuing demand for its use in industrial applications. The fatty acid composition of soybean oil "10.6% palmitic acid; 2.4% stearic acid; 23.5% oleic acid; 51.2% linoleic acid; 8.5% linolenic acid; and 3.8% other" by weight [2]. Soybean oil derivatives containing a Schiff base (SOS-B) were prepared and evaluated as microbial corrosion inhibitors against sulfate-reducing bacteria using the gram-positive Desulfosporosinus orients bacteria as a representative bacterium [3].

Corrosion is the damage to metal caused by reaction with its environment. "Damage" is specified purposely to exclude processes, such as chemical milling, anodizing of aluminum, and bluing of steel, which modify the metal intentionally. Rusting is a type of corrosion but it is the corrosion of ferrous metals (irons and steels) only, producing that familiar brownish-red corrosion product, rust. The environment that corrodes a metal can be anything; air, water, and soil are common but everything from tomato juice to blood contacts metals, and most environments are corrosive. Corrosion is a natural process for metals that causes them to react with their environment to form more stable compounds [4].

Corrosion inhibitor is a chemical added to the corrosive environment in small amounts to reduce the corrosion rate. Some inhibitors interfere with the anode reaction, some with the cathode reaction, and some with both. They are usually used to prevent general corrosion but most are not effective in preventing localized attack, such as crevice corrosion, pitting, or SCc. Inhibitors generally interact with the metal surface in some way: to form a barrier film of adsorbed inhibitor that may be only a monolayer or less, or to form a thick barrier layer of reaction products or inhibitor [5-12]. Organic Adsorption Inhibitors that coat metal with an oily surface layer will protect it. The inhibition property of these compounds is attributed to their molecular structure. The planarity and the lone pairs of electrons in the heteroatoms are important features that determine the adsorption of these molecules on the metallic surfaces. They can adsorb on the metal surface, block the active sites on the surface and thereby reduce the corrosion rate [13-16]. These inhibitors are commonly used in acids, although a few function in neutral or alkaline solutions. In adsorbing on the metal, they replace adsorbed water molecules and prevent water from solvating metal ions or prevent H<sup>+</sup> ions from adsorbing at cathode sites where reduction to H<sub>2</sub> (g) could occur [17,18].

In the present work Gabriel method was used for synthesizing of four different types of green aminated soybean derivatives. The prepared compounds were characterized using FT-IR, and 1H-NMR. The prepared compounds were evaluated as corrosion inhibitors for mild steel using 0.5 N HCl by weight loss method and chemical analysis method. The effect of temperature was also studied.

#### MATERIALS AND METHODS

#### Experimental

#### Brominating of soybean oil

One mole of soybean oil (87.8 g) was placed in round bottom flask, and six moles of bromine (95.88 g) were placed in quick fitted dropping funnel. The bromine solution was allowed to react drop by drop, until the end of bromine addition, with continuous stirring in an ice bath. The obtained product is mentioned at **Scheme 1**.



Scheme 1: Brominated soybean.

#### Synthesis of novel green corrosion inhibitors based on soybean oil

#### Synthesis of corrosion inhibitor (S<sub>1</sub>)

In 250 mL round bottom flask, about (18.368 g) of brominated soybean oil, (7.2 g) of urea, 10 mL of acetone and 3 mL of NaOH were placed [19]. The flask was connected with quick fitted condenser and enabled to reflux using heating mantel at 75°C, for 1 h, **Scheme 2**.



Scheme 2: Aminated derivatives of soybean oil.

Pelagia Research Library

# Synthesis of corrosion inhibitor (S<sub>2</sub>)

In 250 mL round bottom flask, about (18.368 g) of brominated soybean oil, (9.13 g) of thiourea, 10 mL of acetone and 3 mL of NaOH were placed. The flask was connected with quick fitted condenser and enabled to reflux using heating mantel at 75°C, for 1 h, **Scheme 2** [19].

# Synthesis of corrosion inhibitor (S<sub>3</sub>)

In 250 mL round bottom flask, about (18.368 g) of brominated soybean oil, (16.45 g) of 3-amino benzoic acid, 10 mL of acetone and 3 mL of NaOH were placed. The flask was connected with quick fitted condenser and enabled to reflux using heating mantel at 75°C, for 1 h, **Scheme 2** [19].

# Synthesis of corrosion inhibitor $(S_4)$

In 250 mL round bottom flask, about (18.368 g) of brominated soybean oil, (12.85 g) of p-toluidine, 10 mL of acetone and 3 mL of NaOH were placed. The flask was connected with quick fitted condenser and enabled to reflux using heating mantel at 75°C, for 1 h, **Scheme 2** [19].

# Elucidation of chemical structure of the prepared compounds

# Using FT-IR

The prepared compounds were elucidated using Nicolet iS10-FT-IR Spectrophotometer, KBr, Jazan University, Saudi Arabia.

# Using <sup>1</sup>H-NMR.

The structure of the prepared corrosion inhibitors were elucidated using Proton Nuclear Magnetic Resonance "<sup>1</sup>H-NMR" spectra using a 500 MHz (JEOL NMR ECA-500) using DMSO-d6 as a solvent, NRC, Dokki, Egypt.

# Corrosion studies.

# Weight Loss Measurements

Mild steel coupons having chemical composition mentioned in **Table 1**, with dimensions  $7.0 \times 5.0 \times 0.3$  cm were abraded using different grades of emery papers grades (310, 410, and 610), washed with bidistilled water, degreased with acetone, dried and kept in a desiccator. Weigh accurately using a digital balance with high sensitivity. The coupons were immersed in 0.5 N HCl solution with and without various concentrations (250, 500, 1000, 2000, and 3000) ppm of the prepared inhibitors, separately for 3 hours, at different temperatures (308, 318, 328 and 338 K). Weight loss experiments were carried out according to the ASTM standard procedure described in reference [20]. In brief, mild steel specimens in triplicate were immersed in 100 mL 0.5 N HCl containing various concentrations of the studied inhibitors. The mass of the specimens before and after immersion was determined using an analytical balance accurate to 0.01 mg. Reading were taken after each one hour, the coupons were washed with bidistilled water, dried and weighed accurately [21-28]. The investigations carried out in the open air. For further data processing, the average of the three replicate values was used. The pre-cleaned and weighed coupons were suspended in beakers containing the test solutions using glass hooks and rods. The weight loss was calculated by the following equation:

|--|

Element	С	Mn	Р	S	Si	Fe
Ratio (%)	0.11	0.45	0.04	0.05	0.25	99.10
			1			

# $\Delta W = W_1 - W_2$

Where W<sub>1</sub> and W<sub>2</sub> are the weight of coupons before and after immersion.

The surface coverage area ( $\theta$ ) for the different concentrations of the prepared corrosion inhibitors in 0.5N HCl was calculated according to the following equation:

$$\theta = 1 - W_1 / W_2 \tag{2}$$

The inhibition efficiency according to weight loss method  $IE_w$  (%) was determined by the following equation:

IEw%=
$$(W_{corr}/W_{corr}) \times 100$$

284

(3)

(1)

(4)

Where  $W_{corr}$  and  $W_{corr}$  are the corrosion rates of coupon with and without corrosion inhibitors, respectively.

The corrosion rate (CR) was calculated by the following equation:

Where  $W_1$  and  $W_2$  are the weight of coupons before and after immersion in test solutions. A is the total area of the coupon (cm<sup>2</sup>), and t is the immersion time (h).

Chemical analysis of solution according to weight loss method

When a metal undergoes corrosion in an electrolyte of a fixed volume, cations of corroding metal will accumulate in solution. Accordingly, the solution becomes more concentrated in the dissolved cation with the progression of time [29]. Thus, chemical analysis of withdrawn aliquots of the solution as a function of time allows determination of the corrosion rate according to equation (5).

$$CRFe\left(\frac{g}{cm2.h}\right) = \left(\frac{[Fe+3]mole}{cm2.h}\right) \left(\frac{1moleFe}{1mole[Fe+3]}\right) \left(\frac{55.85\,gFe}{1moleFe}\right)$$
**RESULTS AND DISCUSSION**
(5)

# Elucidation of the prepared Corrosion inhibitors

The prepared brominated soybean (S) was elucidated using Fourier transform infrared spectroscopy (FT-IR), **Figure 1**. There was a different peak than soybean oil located at 758 cm<sup>-1</sup> corresponding to C–Br, and disappearance of peak at 1638 cm<sup>-1</sup> corresponding to C=C bond was noticed. FT-IR spectra corresponding to the four prepared corrosion inhibitors (S<sub>1</sub>-S<sub>4</sub>), showed the disappearance of C–Br at 758 cm<sup>-1</sup> and appearance of one peak at 3446 cm<sup>-1</sup> corresponding to secondary –NH group. The presence of peak at about 1740 cm<sup>-1</sup> insures the stability of ester group toward reaction with amines. <sup>1</sup>H-NMR analysis of the brominated soybean (S) and the aminated soybean derivatives (S<sub>1</sub>-S<sub>4</sub>) are mentioned at **Table 2**.



Figure 1: FT-IR of soybean oil, brominated soybean, and S<sub>3</sub> aminated derivative of soybean.

Table 2: <sup>1</sup> H-NMF	R data of the	e prepared (S)	) and (S	$-S_4$ )	compounds
-----------------------------	---------------	----------------	----------	----------	-----------

Compound digestion	Group	ppm
S	СН,	0.8
	CH J)n	1.29
	CH,-CH-Br	1.79
	CO-CH,	2.25
	CH-Br	3.38
	сн,-о	4.45; 4.20
	СН-0-	5.15

 $CR=(W_1-W_2)/At$ 

S <sub>1</sub>	СН <sub>3</sub> (CH <sub>2</sub> )n CH <sub>2</sub> -O CH-O- CH-N- NH NH,	0.96 1.29 4.32 5.15 4.20 6.00 6.00
\$ <sub>2</sub>	CH <sub>2</sub> )n (CH <sub>2</sub> )n CH-O CH-O- CH-N- NH NH <sub>2</sub> NC-CH <sub>2</sub> -C-N CO-CH <sub>2</sub>	0.96 1.29 4.32 5.15 2.84 2.00 2.00 1.73 2.25
S <sub>3</sub>	CH <sub>3</sub> (CH <sub>2</sub> )n CH <sub>2</sub> -O CH-O- CO-CH <sub>2</sub> CH Aromatic OH	0.96 1.29 4.32 5.15 2.25 6.77 11
S <sub>4</sub>	CH <sub>3</sub> (CH <sub>2</sub> )n CH <sub>2</sub> -O CH-O- CO-CH <sub>2</sub> CH Aromatic Ph-CH <sub>3</sub> CH-N	0.96 1.29 4.32 5.15 2.25 6.84; 6.31 2.35 2.84

# **Corrosion tests**

#### Weight loss method

The inhibition efficiency of the organic compounds depends on many factors including the number of adsorption sites and their charge density, molecular size, heat of hydrogenation, mode of interaction with the metal surface and formation of metallic complexes [8]. Weight loss parameters were mentioned at **Table 3**.

**Table 3:** Weight loss parameters of mild steel (CS-37) treated without and with the prepared corrosion inhibitors  $(S_1-S_4)$  at 308 K.

Inhibitor	Concentration "ppm"	Total weight loss (mg)	Corrosion Rate (mg.cm <sup>-2</sup> .h- <sup>1</sup> )	Surface Coverage (θ)	IE %
Blank	0	650	6.19	-	-
S <sub>1</sub>	3000	42.57	0.4054	0.9345	93.45%
	2000	54.46	0.5187	0.9162	91.62%
	1000	81.24	0.7737	0.875	87.50%
	500	95.99	0.9142	0.8523	85.23%
	250	100	0.952	0.846	84.62%
S <sub>2</sub>	3000	33.9274	0.3231	0.9478	94.78%
	2000	42.5067	0.4048	0.9346	93.46%
	1000	53.56	0.51	0.9176	91.76%
	500	63.695	0.6066	0.902	90.20%
	250	73.05	0.6957	0.8876	88.76%
S <sub>3</sub>	3000	29.505	0.281	0.9546	95.46%
	2000	32.63	0.3107	0.9498	94.98%
	1000	43.87	0.4178	0.9325	93.25%
	500	51.996	0.4952	0.92	92%
	250	56.868	0.5416	0.9125	91.25%
S <sub>4</sub>	3000	21.5783	0.2055	0.9668	96.68%
	2000	28.0778	0.2674	0.9568	95.68%
	1000	37.827	0.3602	0.9418	94.18%
	500	49.00	0.4667	0.9246	92.46%
	250	53.68	0.5113	0.9174	91.74%

#### Effect of $(S_1-S_4)$ concentrations

The variation of inhibition efficiency (IE<sub>w</sub>%) from weight loss measurements with ( $S_1$ - $S_4$ ) concentrations is shown in **Figure 2**. It was found that the weight loss parameters; "corrosion rate CR, surface coverage  $\theta$ , and percentage of inhibition efficiency" increases with increasing ( $S_1$ - $S_4$ ) concentration and record the maximum value (93.63%  $S_1$ , 94.78%  $S_2$ , 95.46% for  $S_3$  and 96.68% for  $S_4$ ) of inhibition efficiency at 3000 ppm concentration. The inhibition efficiency of the prepared additives increases in the order  $S_4$ > $S_3$ > $S_2$ > $S_1$ . The highest inhibition efficiency of inhibitor  $S_4$  may be attributed to the presence of (methyl group) electron donating group.



Figure 2: Variation of inhibition efficiency with different concentrations of the prepared inhibitors  $(S_1 - S_4)$  in 0.5 N HCl at 308 K.

# Effect of temperature

In order to calculate the activation energy (Ea) of the corrosion process and investigate the mechanism of inhibition, weight loss measurements were performed in the temperature range of 308-338 K in absence and presence of 3000 ppm of the prepared inhibitors ( $S_1$ - $S_4$ ) at 0.5 N HCl. It was found that the corrosion rate of mild steel increases with increasing temperature. The results indicates that increasing temperature leads to a decrease of RT, hence increasing the corrosion rate of carbon steel as shown in **Figure 3**. A plot of ln corrosion rate (ln k) against the reciprocal of absolute temperature (1/T) was drawn graphically to obtain activation energy Ea, according to Arrhenius equation:



Figure 3: Variation of RT values of carbon steel with 3000ppm of  $(S_1 - S_4)$  inhibitors at different temperatures

#### ln K=-Ea/RT+constant

Where Ea equal to slope of this equation.

#### Adsorption isotherm

To understand the corrosion inhibition mechanism, the organic compound's adsorption behaviour on the carbon steel

(6)

surface must be known. The plot of  $C_{inh}/\Theta$  vs.  $C_{inh}$ , Figure 4 yielded a straight line, proved that the adsorption of the prepared corrosion inhibitors from the hydrochloric acid solution obeys Langmuir adsorption isotherm, which is presented by equation (7) [27].



Figure 4: Langmuir isotherms for the adsorption of the prepared corrosion inhibitors on carbon steel surface in 0.5 N HCl at 308 K

$$C_{inh}/\theta = (1/K_{ads}) + C_{inh}$$
<sup>(7)</sup>

Where  $C_{inh}$  is the inhibitor concentration and  $K_{ads}$  is the equilibrium constant for the adsorption/desorption process. From the intercepts of the straight lines on the  $C_{inh} / \Theta$  - axis, one can calculate  $K_{ads}$ , which is related to the standard free energy of adsorption,  $\Delta G_{ads}$ , as given by Eq. (8) [28]:

$$\Delta G_{ads} = -RT \left( \ln^{1/10} K_{ads} \times 55.5 \right)$$
(8)

The calculated free energy of adsorption ( $\Delta G_{ads}$ ) is given in **Table 4**. The negative values of  $\Delta G_{ads}$  indicated that the adsorption of the inhibitors on the metal surface is spontaneous. Generally, values of  $\Delta G_{ads}$  around 20 kJ mol<sup>-1</sup> or lower are consistent with the electrostatic interaction between charged molecules and the charged metal surface (physisorption and chemisorption); It can be seen from **Table 4** that, calculated  $\Delta G_{ads}$  values indicated that the adsorption mechanism of the prepared corrosion inhibitors on carbon steel in 0.5 N HCl solution is physical and chemical adsorption. The large values of  $\Delta G_{ads}$  and its negative sign are usually characteristic of strong interaction and a highly efficient adsorption. The aminated derivatives of soybean oil were generally chemisorbed at the metal surface and displace the adsorbed water and electrolytes from the surface. It is assumed that these N-containing functional groups act as electron pair donors to the electron depleted dehydrated metal surface. This interaction between the inhibitor and the metal surface is due to the formation of a bond between the N electron pair and the electron cloud at the surface.

Table 4: Adsorption parameters for the prepared corrosion inhibitors  $(S_1-S_4)$  on mild steel in 0.5 N HCl at 308 K.

Inhibitor	K <sub>ads</sub>	∆G <sub>ads</sub> (KJ/mole)
S <sub>1</sub>	57.798	-20.34
S <sub>2</sub>	30.987	-18.76
S <sub>3</sub>	21.706	-17.87
S <sub>4</sub>	25.353	-18.261

#### CONCLUSION

Four green corrosion inhibitors were prepared via reaction of brominated soybean oil with different types of amines "urea, thiourea, 3- amino benzoic acid and p- toluidine". The aminated derivatives were elucidated using FT-IR and <sup>1</sup>H-NMR, and they were evaluated as corrosion inhibitors for mild steel at 0.5N HCl, using weight loss method and chemical analysis method at different temperatures "308-338" K. It was found that the inhibition efficiency "IE<sub>w</sub>%" increases with increasing the inhibitor concentration, while decrease with rising of temperature and the order of increasing the inhibitors on metal surfaces from 0.5 N HCl solution obeys Langmuir adsorption isotherm. The high value of adsorption equilibrium constant suggested that the prepared organic corrosion inhibitors were strongly chemically and physically adsorbed on the mild steel surfaces. Chemical analysis method was used for the determination of weight of the corroded iron according to weight loss calculations and it was found that the amount of the corroded iron decreases with increasing the increasing concentration, and the order of increasing the corroded iron was as fellow:  $S_1 > S_2 > S_3 < S_4$ .

# Pelagia Research Library

#### ACKNOWLEDGMENT

I would like to thank the management of faculty of science and arts, Samtah, Jazan University for providing me with chemicals and analysis.

#### REFERENCES

- [1] Kaplan DL (1998) Biopolymers from renewable resources. Springer, Verlag Berlin Heidelberg, p. 267.
- [2] Gruber PR, Hall ES, Kolstad JJ, Iwan ML, Benson RD, et al. (1993) US patent 5258488.
- [3] Graiver D, Dacomba R, Khawaji M, Jaros A, Berglund K, et al. (2012) Steel-corrosion inhibitors derived from soybean Oil. J Am Oil Chem Soc 89:1895-1903.
- [4] Bradford SA (1993) Corrosion control, Van Nostrand Reinhold, New York, pp.1-238.
- [5] Khamis E (1990) The effect of temperature on the acidic dissolution of steel in the presence of inhibitors. *Corrosion* 46: 476-484.
- [6] Pierre RR (2000) Handbook of Corrosion Engineering, McGraw-Hill Companies, Inc., 833-861.
- [7] Quraishi MA, Danish J, Saeed MT (2000) Fatty acid derivatives as corrosion inhibitors for mild steel and oil-Well tubular steel in 15% boiling hydrochloric acid. JAOCS 77: 265-268.
- [8] Mouayed YK, Abdulsada AM, Alshawi JMS (2014) Synthesis, identification and the study of some new azo dyes as corrosion inhibitors for copper in (1m) HCl. *Journal of Basrah Researches (Sciences)* 40: 108-127.
- [9] Afolabi AS, Muhirwa AC, Abdulkareem AS, Muzenda E (2014) Weight loss and Microstructural Studies of Stressed Mild Steel in Apple Juice. Int J Electrochem Sci 9: 5895-5906.
- [10] El-Etre AY (2003) Inhibition of aluminum corrosion using opuntia extract. Corrosion Science 45: 2485-2495.
- [11] El- Naggar (2006) Corrosion inhibition of mild steel in acidic medium by some sulfa drugs compounds. Corros Sci 49: 2226-2236.
- [12] Growcock FB, Lopp NR, Jasinski R (**1988**) Kinetics of steel corrosion in hydrochloric acid inhibited with trans-cinnamaldehyde. *J Electrochem Soc* 135: 823-827.
- [13] Gad Alla AG, Tamous HM (1990) Structural investigation of pyrazole derivatives as corrosion inhibitors for delta steel in acid chloride solutions. J Appl Electrochem 20: 488-493.
- [14] Agrawal R, Namboodhiri TKG (1990) The inhibition of sulphuric acid corrosion of 410 stainless steel by thioureas. *Corros Sci* 30: 37-52.
- [15] Moretti G, Quartarone G, Tassan A, Zingales A (1996) 5-Amino- and 5-chloro-indole as mild steel corrosion inhibitors in 1 N sulphuric acid. *Electrochem Acta* 41: 1971-1980.
- [16] Kuznetsov YI (1996) Organic inhibitors of corrosion of metals. Springer Science & Business Media, pp. 1-283.
- [17] Agrawal R, Namboodhiri TKG (1997) Inhibition of corrosion and hydrogen embrittlement of a HSLA steel in 0.5M H<sub>2</sub>SO<sub>4</sub> by nitrile compounds. J Appl Electrochem 27: 1265-1274.
- [18] Abdel-Aal MS, Morad MS (2001) Inhibiting effects of some quinolines and organic phosphonium compounds on corrosion of mild steel in 3M HCl solution and their adsorption characteristics. *Br Corros J* 36: 253-260.
- [19] Nasser RM (2017) Investigation of the behavior of aminated jojoba derivatives as green corrosion inhibitors for Mild Steel at 0.5 N HCl. Der Chemica Sinica 8: 123-132.
- [20] ASTM G 31-72, standard practice for laboratory immersion corrosion testing of metals (1990) West Conshohocken, PA, USA.
- [21] Mthar M, Ali H, Quraishi MA (2002) Corrosion inhibition of carbon steel in hydrochloric acid by organic compounds containing heteroatoms. Br Corros J 37: 155-158.
- [22] Selvi ST, Raman V, Rajendran N (2003) The performance of a migrating corrosion inhibitor suitable for reinforced concrete. J Appl Electrochem 33: 1182-1189.
- [23] Bentiss F, Traisnel M, Vezin H, Hildebrand HF, Lagrenee M (2004) 2,5-Bis(4-dimethylaminophenyl)-1,3,4- oxadiazole and 2,5-bis(4-dimethylaminophenyl)- 1,3,4-thiadiazole as corrosion inhibitors for mild steel in acidic media. *Corros Sci* 46: 2781-2792.
- [24] Noor EA (2005) The inhibition of mild steel corrosion in phosphoric acid solutions by some N-heterocyclic compounds in the salt form. *Corros Sci* 47: 33-55.
- [25] Yurt A, Bereket G, Balaban AB, Erk E (**2005**) Effect of schiff bases containing pyridyl group as corrosion inhibitors for low carbon steel in 0.1 M HCl. *J Appl Electrochem* 35: 1025-1032.
- [26] Li X, Tang L, Li L, Mu G, Li G (2006) Synergistic inhibition between o-phenanthroline and chloride ion for steel Corrosion in sulphuric acid. *Corros Sci* 48: 308-321.
- [27] Al-Sabagh AM, Kandile NG, Nasser NM, Mishrif MR, El-Tabey AE (2013) Novel surfactants incorporated with

1,3,5-triethanolhexahydro-1,3,5-triazine moiety as corrosion inhibitors for carbon steel in hydrochloric acid: Electrochemical and quantum chemical investigations. *Egypt J Pet* 22: 351-365.

- [28] Al-Sabagh AM, Abd-El-Bary HM, El-Ghazawy RA, Mishrif MR, Hussein BM (2011) Corrosion inhibition efficiency of linear alkyl benzene derivatives for carbon steel pipelines in 1M HCl. *Egypt J Pet* 20: 33-45.
- [29] McCafferty E (2010) Introduction to corrosion Science; Springer Science and Business Media LLC, 119-175.