Available online at www.pelagiaresearchlibrary.com



Pelagia Research Library

Der Chemica Sinica, 2014, 5(1):47-54



Thermal and mechanical properties of modified polyester resin and jute composite

R. B. Patel, K. S. Patel, R. N. Patel and K. D. Patel

Chemistry Department, Shree P. M. Patel Institute of P.G. Studies and Research in Science, Sardar Patel University, Anand, Gujarat- India

ABSTRACT

Unsaturated polyester resin has been synthesized using phthalic anhydride, maleic anhydride, propylene glycol and adipic acid. Synthesized unsaturated polyester resin, stryrine and jute fiber along with benzoyl peroxide as catalyst were used for the composite preparation. Mechanical and thermal properties of composites were evaluated. The results indicate the good thermal stability of some compounds. The obtained composites were characterized by TGA & DSC. The DSC scans of resins are analyzed by the method proposed by Borchardt and Daniels

Keywords: Unsaturated polyester resin, Mechanical properties, TGA & DSC

INTRODUCTION

Polymers square measure substances whose molecules accommodates an oversized range of units of a number of types: the units themselves, consisting of variety of atoms, square measure typically noted because the segments of the chemical compound. within the chemical change of a combination of 2 monomers, the structure of every molecule contains units of each monomers. Such a chemical compound is termed polymer and therefore the method of its synthesis is termed copolymerization. they're wide used commercially as fibers, plastics, composites and for coatings applications too [1-3]. they're heterochain macromolecules that possess process organic compound teams as associate integral element of their chemical compound backbones. They take issue from alternative organic compound containing polymers (such as polyacrylates and polysaccharide organic compounds) therein the ester practicality is an element of the backbone and not a pendant cluster.

Polyesters [4-6] area unit one amongst the foremost versatile artificial copolymers. Polyesters area unit created in high volume that exceeds thirty billion pounds a year worldwide [6].

The first unsaturated polyester resins of comparable kind as used nowadays were synthesized within the 1930's. Carlton Ellis found that unsaturated polyester prepolymers might be mixed with phenylethylene|vinyl resin|polyvinyl resin} and copolymerized into a rigid polymer. These resins became commercially necessary consecutive decade once they were strengthened with glass fibers giving structural merchandise with high mechanical strength and tenuity. nowadays unsaturated polyesters area unit one amongst the foremost necessary matrix resins for composite materials [7].

R. B. Patel et al

Composites area unit those materials shaped by positioning extraordinarily sturdy and stiff continuous or shredded fibers in a very compound organic compound matrix or binder. The fibers build them useful; the fibers area unit usually fifty times stronger and 20-25 times stiffer than the matrix polymers. The role of matrix is primarily that of a glue or binder that permits the fibers to support the applied load. Fibers area unit combined with a organic compound and laminated to support the applied load. several laminates exhibit mechanical properties adequate or olympian those of most metals [8].

In gift study Unsaturated polyester organic compound has been synthesized mistreatment anhydride, maleic chemical compound, propanediol and hexanedioic acid. Synthesized unsaturated polyester organic compound, stryrine and jute fiber beside blanching agent as catalyst were used for the composite preparation. Mechanical and thermal properties of composites were evaluated

Characterization of resin & composite

Reaction was monitored by continues determination of the reaction mass. Completion of reaction was observed with FTIR and was compared data with a standard (Table-1 & Fig.1). The obtained composites were characterized by TGA & DSC (Fig. 2 & 3).

No.	Group	IR Characteristics (cm ⁻¹)	IR for UPR-S1
Α	Esters α, β - unsaturated >C=O stretching	1730 - 1715	1729.00
В	C-H Stretching in aromatic	3030	2985.19
С	C-C multiple bend stretching in aromatic	1600	1600.16
D	Hydrocarbon Alkane –CH2-	1445-1485	1454.35
Е	Alcohols O-H bond stretching	1260-1350	1283.63
F	C-H stretching in aromatic ring (O- disubstituted)	735-770	743.78

Table 1. Infrared spectra of UPR-S1



Figure 1. Infrared spectra of UPR-S1

MATERIALS AND METHODS

Phthalic anhydride, maleic anhydride, propylene glycol and adipic acid were obtained from Chiti –Chem Corp. Ltd, Vadodara. All the chemicals used were of analytical grade.

Synthesis Of Unsaturated Polyester Resin

Almost all commercial production of unsaturated polyesters is done by the melt polycondensation of unsaturated and saturated acids or anhydrides with glycols. No solvents are used and the formed water is continuously removed, in order to force the esterification reaction towards completion. The condensation temperature is typically between $170-230^{\circ}$ C. At the end of the condensation, vacuum is often applied in order to remove remaining water from the viscous melt. The total reaction time can be from 8 to 25 hrs, and the reaction is followed by acid number titrations and viscosity measurements.

Azeotropic polycondensation in the presence of organic solvents such as xylene or toluene can also be used. The reaction takes place at lower temperatures and it is possible to avoid losses of volatile reactants. The drawbacks are longer reaction times and environmental problems with solvent removing and recycling. Polyester resins were prepared in the present work by the technique reported by B.Parkyn [9]. A mixture of Propylene glycol (PG), Phthalic anhydride, mailic anhydride, p- Toluene sulfonic acid (PTSA) and Xylene as distillating solvent was charged in a four - neck reaction kettle equipped with stirrer, thermometer, nitrogen-gas introducing tube, Dean & Stark apparatus and watercondenser. The mixture was mechanically stirred and heated at 140-200^oC under nitrogen gas stream and esterification was carried out while removing water formed by the reaction from the reaction system, continues heating at 140-200^oC until an acid number of 25-30 were reached. The Xylene was completely distilled out and reaction product was allowed to cool.

The details about the molar ratio of acids/anhydrides to glycols, styrene monomer and reaction temperature for the synthesis of the unsaturated polyester resins (UPR) are as shown in the Table 2



Scheme 1: Reaction mechanism for UPR-S1



Scheme-2. Reaction mechanism for AAMUPR-S11-S14



Scheme-3: Reaction mechanism for AAMUPR-S15

Table 2. Composition and reaction temperature for unsaturated polyester resin (UPR-S1)

SAMPLE: S1							
MONOMERS	MOLECULAR Wt. gm/mole	MOLES gm	WEIGHT gm	Wt. OF 100% BASIS IN gm			
P.A	148.12	0.5	74.06	33.36			
M.A	98.06	0.5	49.03	22.08			
P.G	76.10	1.3	98.93	44.56(43.01 ml)			
TOTAL Wt.	-	-	222.02	99.99			
* PTSA = 2%/100gm = 2.0 gm							
* Weigh = Molecular Wt. x Moles $* \rho = m/v$							

Composite Fabrication

Two basic methods are generally used for the fabrication of composites, which are known as wet and dry lay-up lamination. Wet lay-up method implies the use of liquid resins to impregnate the matrix material either before or after it has been laid in place. In case of conventional dry-up method the reinforcement is impregnated with a solution of the resin in appropriate solvent and the solvent evaporated or flushed off and the result is dry resin impregnated sheet known as a prepreg which is used to prepare composites [10]. Laminating is normally carried out manually by brush, roller or squeezer application to glass fiber [11]. The composites were made by using glass fiber and various resin systems. In present study the compositions used for the composites preparation are shown in Table 3

Table: 3 Composition of composites

SampleUPR	Jute (40%) in	SDUPR (60%) in	Total Weight in	BPO (2% of total Wt)	Cureing Temp. in	Cureing time in
&	gms	gms	gms	in gms	°C	hrs.
S1	36.20	54.30	90.50	1.81	100-110	2
S11	35.40	53.10	88.50	1.77	100-110	2
S12	35.15	52.73	87.88	1.76	100-110	2
S13	35.72	53.58	88.41	1.77	100-110	2
S14	35.03	52.55	87.58	1.75	100-110	2
S15	31.92	47.88	79.80	1.60	100-110	2

S1: unsaturered polyester resin(UPR-S1),

S11-S15: Adipic acid modify unsaturered polyester resin (AAMUPR-S11-S15)

The resin composition containing styrene as cross liking agent and benzoyl peroxide as a catalyst and applied to 6×6 inch square pieces of jute with brush. The solvent allowed evaporating at 50°C. The dried eight prepregs prepared in this way were stacked one over another and pressed between two plates using Teflon sheets as mould releasing agent. The plates were compressed under 95-100 psi at specified temperature (110-110°C) and then kept in an oven maintained at required temperature for two hours. The composites so obtained were cooled to room temperature before releasing the pressure. All the composites were prepared by the same procedure. The specimens for testing

R. B. Patel et al

were made by cutting the composites and matching them to required final dimensions. All the tests were conducted according to ASTM methods.

RESULTS AND DISCUSSION

The IR spectra of cured unsaturated polyester resins are as shown in Fig. 1. The data regarding the IR spectral characteristics presented in Table 1. reveals that small variations in the location of the peaks due to absorptions by functional groups like $-CH_2$ and C=O are observed depending upon the structure of the diols/ anhydrides/acids.

For UPR-S1, a strong absorption band at 743.78 cm⁻¹ can be arributed to -C-H stretching in aromatic ring (O-disubstituted). Spectrum absorption bend at 1729.00 cm⁻¹ & 2985.19 cm⁻¹ confirms the presence of α , β -unsaturated >C=O bond in ester linkage & C-H stretching in aromatic respectively. Absorption peak dose not appearing at 1652 cm⁻¹ for C-C multiple bond stretching in alkene after curing of UPR-S1, so it was missing in Table 1. Spectrum absorption bend at 1600.16cm⁻¹ was C-C multiple bend stretching in aromatic. Alkane $-CH_2$ - & O-H bond stretching was confirmed by the presence of bend at 1454.35 cm⁻¹ and 1283.63 cm⁻¹ respectively.

For AAMUPR-S11, a strong absorption band at 748.70 cm⁻¹ can be arributed to -C-H stretching in aromatic ring (O-disubstituted). Spectrum absorption bend at 1728.00.cm⁻¹ & 3025.10 cm⁻¹ confirms the presence of α,β -unsaturated >C=O bond in ester linkage & C-H stretching in aromatic respectively. Absorption peak appearing at 1605.60 cm⁻¹ was C-C multiple bend stretching in aromatic. Alkane $-CH_2$ - & O-H bond stretching was confirmed by the presence of bend at 1456.30 cm⁻¹ and 1285.66 cm⁻¹ respectively.



Figure:	2 DSC	Scan of	UPR-S1
----------------	-------	---------	--------

Table: 4: TGA of UPR-S1-S15

Sampla	% Weight loss at various Temperature (^o C) from TGA							
Sample	100	200	300	400	500	600	700	800
S1	0.38	7.68	47.51	86.66	88.54	89.24	90.42	92.22
S11	0.59	5.63	26.31	88.82	90.45	91.26	92.93	95.70
S12	0.59	4.53	24.04	89.05	90.70	91.39	92.71	94.36
S13	0.59	3.42	21.76	89.27	90.96	91.59	92.79	94.45
S14	0.70	3.08	17.62	89.96	91.70	92.40	93.56	95.55
S15	0.88	2.75	13.50	90.63	92.59	93.41	94.51	96.54



Figure: 3: TGA Scan of UPR-S1

The synthesized polyester resins were cured by DSC technique using benzoyl peroxide as catalyst.

The TA Instruments, USA model 5000/2920 differential scanning calorimetry was used to obtain the data on the exothermic curing reactions. The sample weights used for the investigation were in the range of 8 - 10mg.

The DSC scans of resins are analyzed by the method proposed by Borchardt and Daniels [12].

The results of DSC study (Table 4.) shows that the curing reaction starts at or above 100°C and gets completed almost around 142°C. This clearly indicates that the unsaturated polyester resins have good induction period under this condition and therefore it can be expected that at room temperature the unsaturated polyester resins would have a very long induction period which is needed for better safe storage stability.

The curing range is of 43°C to 44°C which indicates that after initiation of curing actual curing gets completed within 4.4 min which is also very good indication of processing time for which unsaturated polyester resins are to be kept under compression during compression moulding process. The kinetic parameters indicate the heat of reaction of UPR-S1 (40.7 J/gms).

The TGA data in table 2. indicates that the thermal stability increases when phthalic anhydride is replaced by adipic acid up to 300°C temperature. AAMUPR-S15 (without phthalic anhydride) is thermally more stable then UPR-S1 (without adipic acid). After 300°C temperature, thermal stability is approximately similar for UPR & AAMUPR.

Mechenical Property

Flexural properties

Flexural properties were carried out in terms of stress-strain relationship using standard method of testing ASTM D-790[13]. A Dutron's Tensile Tester Mode l No. 130 was used for the study. A strip of the dimensions 8.0 x 1.25 cm2 131 was cut from the laminate for measurement. It suited the gauge length of 7.5 cm i.e. the experiment was carried out a distance between two jaws to be 7.5 cm apart. The results were recorded with the chart speed of 2 mm/min at room temperature. The test was initiated by applying the load to the specimen at the specified crosshead rate. The deflection was measured by gauge under the specimen in contact with it in the center of the support span. The calculation of flexural strength was carried out and the results are included in Table 5.

Izod impact strength

A study on Izod impact strength was carried out in terms of resistance to breakage under high velocity impact conditions, according to ASTM D-256 [14]. The impact test indicates the energy to break standard test specimen of specified size under the stipulated conditions of specimen mounting and pendulum velocity at impact. Zwick mode

R. B. Patel et al

1 No. 8900 Impact Machine was used for the study. All the measurements were carried out at room temperature. For the measurement, a specimen was cut from the fabricated composite $(6.4 \times 1.27 \text{ cm}2146)$ and V notched (2.5 mm) at the middle. The test specimen was clamped into position so that notched end of the specimen remained facing the striking edge of pendulum. All the Izod impact strength data of synthesized composites were given in Table 5.

Rockwell hardness study

The Rockwell hardness study was carried out at room temperature according to standard method of testing ASTM D -785 [15]. In the present study, Rockwell hardness tester model RAS/Saroj Engg. Udyog Pvt. Ltd., Jaysingpur was used. Load of 100kgf was applied for each measurement. The specimen with parallel flat surfaces was placed on the avail of the apparatus and minor load (10kgf) was applied by lowering the steel ball onto the surface of the specimen. The dial was adjusted to zero on the scale under minor load and the major load (100kgf) was immediately applied by releasing the trip lever. After few second the major load was removed and the specimen was allowed to recover for 15 second. Rockwell hardness was read directly on the dial with the minor load still applied. All the mechanical data of synthesized composites were given in Table 5

Table: 5 Flexural Strength & Flexural Modulas (kg/cm ²	Table: 5 Flexural	Strength	& Flexural	Modulas	(kg/cm^2)
---	-------------------	----------	------------	---------	-------------

Sample	Flexural Strangth	Flexural Modulas	Impact Strength J/Cm ²	Rockwell Hardness "M" SCALE
S1	425.44	6412.58	1.60	69
S11	570.77	7508.46	1.84	70
S12	330.50	5019.25	1.75	72
S13	260.49	3708.56	1.72	75
S14	205.50	2827.24	1.65	77
S15	198.06	2816.68	1.63	80

CONCLUSION

Unsaturated polyester resin (UPR-S1) compared with modified unsaturated polyester resin. Flexural Strength & Flexural Modulas of AAMUPR-S11 (adipic acid modified unsaturated polyester resin) is greater than UPR-S1. For AAMUPR-S12 to AAMUPR-S15 the Flexural Strength & Flexural Modulas are lower than UPR-S1.

The Impact Strength of all modified unsaturated polyester resin are incresis if moles of Adipic acid increases, so the Impact Strength of all modified unsaturated polyester resin are higher than the unsaturated polyester resin(UPR-S1). The Rockwell Hardness of AAMUPR is higher than UPR-S1.

Composites of unsaturated polyester resin were synthesized using different monomers having various concentrations. All the composites show good thermal stability. Flexural Strength & Flexural Modulas of AAMUPR-S11 (adipic acid modified unsaturated resin) is greater than UPR-S1.

Acknowledgements

The authors are thankful to Shree P.M.Patel Institute of P.G. Studies and Research in Science (APMS) for providing research facilities .We are thankful to The Director, SICART, Vallabh Vidyanagar for analytical facilities. Authors are also grateful to The Director, SAIF-RSIC, Panjab University, Chandigarh for NMR analysis. We are articulate our appreciation to IIT-Bombay for TG and DTG scan analysis facility.

REFERENCES

[1] I. Goodman; J. A. Rhys; Polyesters; Saturated Polymers; Iliffe Books; London; 1; **1965**.

[2] I. Goodman; 2nd ed; 16: 159; Wiley: New York, **1968**.

[3] P. W. Morgan; Condensation Polymers; By Interfacial and Solution Methods; Inerscience Publishers; New York; **1965**.

[4] Bjorksten Research Laboratories; Polyesters and Their Applications; Reinhold; New York; 1956.

[5] V. V. Karshak and S. V. Vinogradova; Polyesters; Pergamon; New York; 1965.

[6] I. Goodman; Encyclopedia of Polymer Science and Engineering; 2nd ed.; 12; Wiley; New York; **1988**.

[7] O. C. Zaske and S. H. Goodman; Unsaturated Polyester and Vinyl Ester Resins, in: S. H. Goodman; (Ed.); Handbook of Thermoset Plastics; 2nd Ed.; Noyes Publication, Westwood pp 97; **1998**.

[8] "Composites" Encyclopedia of polymer science and engineering; 2nd ed. By Jacque line I. Kroschwitz; A Wiley inter science publication N. Y.; 13; 776-820; **1985**.

[9] B. Parkyn; F. Lamb; and B. V. Clifton; "Polyesters -Unsaturated Polyesters and Polyester Plasticizers"; Iliffe books Ltd; London; 2; 17; **1967**

[10] G. M. Bartenev; Chem. Engr. No. ; 182; CE 249; 1964; CA 62 3778d; **1965**.

[11] R. H. Norman and D. I. James; Chem. Engr. No.; 182; CE 243; 1964; CA 62 1790h; 1965.

[12] B. Jalajakumari; K. G. K. Warrier; K. G. Satyanarayana and C. Pavithran; *Journal of Reinforced Plastics and Composites*; 7(5); 402-412; **1988**.

[13] F.A. Mayers, Paper No.1-D Presented at 37th Annual Conference SPI, Washington, D.C., January 11-15 (1982).

[14] ASTM D-256, Impact Resistance of Plastics and Electrical Insulating Materials, (1984).

[15] ASTM D-785, Rockwell Hardness of Plastics and Electrical Insulating 233 Materials, (1965).