

February 19-20, 2019
Prague, Czech RepublicJ Org Inorg Chem 2019, Volume: 5
DOI: 10.21767/2472-1123-C1-021

CONTROLLED SYNTHESIS AND LAYER-NUMBER-DEPENDENT CATALYTIC PROPERTIES OF FEW-LAYERED MoS_2/CdS VAN DER WAALS HETEROSTRUCTURES FOR EFFICIENT PHOTOCATALYTIC H_2 EVOLUTION

Shahid Iqbal

Xi'an Jiaotong University, China

In a typical photocatalytic reaction, efficient solar light harvesting and charge generation, as well as effective charge transport, are key factors that determine the efficiency of the photocatalytic system for H_2 production. Atomically layered heterostructures have attracted significant research interest due to their unique layer-dependent catalysis and electronic properties. Previous studies have reported that the catalytic properties of MoS_2 layered materials are highly dependent on the number of layers, and the difficulty of controlling the number of layers over a substrate has been a bottleneck for widespread use. Therefore, developing a simple, facile and environmentally friendly method to fabricate van der Waals heterostructures (vdWHs) with precisely controlled MoS_2 layers for achieving highly efficient H_2 generation is still a challenge. Here, we report for the first time that the H_2 bubbles generated by photocatalytic water splitting are effective in the layer-by-layer exfoliation of MoS_2 nanocrystals (NCs) into few layers (Figure 1). The as obtained few layers can be *in situ* assembled with CdS nanosheets (NSs) into vdWHs of few-layered MoS_2/CdS NSs which, in turn, are effective in charge separation and transfer, leading to enhanced photocatalytic H_2 production activity. The few-layered MoS_2/CdS vdWHs exhibited a H_2 evolution rate of $140 \text{ mmol g}(\text{CdS})^{-1} \text{ h}^{-1}$ and achieved an apparent quantum yield of 66% at 420 nm. This study provides a new strategy for the design of noble-metal-free few-layered MoS_2/CdS vdWH systems for photocatalytic H_2 generation. We believe that this bubble exfoliation strategy can be extended to a range of other layered transition metal dichalcogenide compounds

shahidiqbal@mail.xjtu.edu.cn




Figure 1: Schematic illustration of the exfoliation of MoS_2 nanocrystals and the fabrication of vdWHs of few-layered MoS_2/CdS nanosheets by bubble exfoliation